

CASING STRENGTHS INFORMATION

Source: Halliburton Cementing Tables

<u>Casing Size</u>	<u>Weight</u>	<u>Grade</u>	<u>Strengths</u>
5-1/2"	20#	S-95	Burst Press = 10,910 psi Collapse Press = 10,000 psi
7-5/8"	39#	S-95	Burst Press = 10,900 psi Collapse Press = 9,980 psi