

STATE OF NEW MEXICO
ENERGY AND MINERALS DEPARTMENT

NO. OF COPIES RECEIVED	
DISTRIBUTION	
SANTA FE	
FILE	
U.S.O.S.	
LAND OFFICE	
OPERATOR	

OIL CONSERVATION DIVISION
P. O. BOX 2088
SANTA FE, NEW MEXICO 87501

Form C-103
Revised 10-1-78

5a. Indicate Type of Lease
State ☐ Fee ☒

5. State Oil & Gas Lease No.
-

SUNDRY NOTICES AND REPORTS ON WELLS

(DO NOT USE THIS FORM FOR PROPOSALS TO DRILL OR TO DEEPEN OR PLUG BACK TO A DIFFERENT RESERVOIR. USE "APPLICATION FOR PERMIT -" (FORM C-101) FOR SUCH PROPOSALS.)

1. OIL WELL <input checked="" type="checkbox"/> GAS WELL <input type="checkbox"/> OTHER <input type="checkbox"/>	7. Unit Agreement Name -
2. Name of Operator Morris R. Antweil	8. Farm or Lease Name Moby
3. Address of Operator P. O. Box 2010, Hobbs, NM 88241	9. Well No. 2
4. Location of Well UNIT LETTER C 1980 FEET FROM THE West LINE AND 830 FEET FROM THE North LINE, SECTION 7 TOWNSHIP 20S RANGE 38E NMPM.	10. Field and Pool, or Wildcat West Nadine Blinebry
11. Elevation (Show whether DF, RT, GR, etc.) 3559.9' GR	12. County Lea

Check Appropriate Box To Indicate Nature of Notice, Report or Other Data

NOTICE OF INTENTION TO:

PERFORM REMEDIAL WORK ☐
TEMPORARILY ABANDON ☐
PULL OR ALTER CASING ☐
OTHER ☐

PLUG AND ABANDON ☐
CHANGE PLANS ☐
OTHER ☐

SUBSEQUENT REPORT OF:

REMEDIAL WORK ☐
COMMENCE DRILLING OPWS. ☐
CASING TEST AND CEMENT JOBS ☐
OTHER ☐

17. Describe Proposed or Completed Operations (Clearly state all pertinent details, and give pertinent dates, including estimated date of starting any proposed work) SEE RULE 1103.

Spudded well 6:30 AM 10/8/84

Drilled 12½" hole to 1450". Ran 39 jts 9 5/8" 36# J-55 casing and cemented at 1450' with 425 sx Halliburton light cement containing 5#/sk gilsonite, ¼#/sk flocele and 2% CaCl₂ and 215 sx class "C" cement containing 2% CaCl₂. Plug down 11:00 AM 10/9/84 WOC 15½ hours. Tested casing to 1500 psi and drilled out with 8 3/4" bit. Mixed 1100 cubic feet slurry, approximate mixing temp 60°F, minimum temp. in zone of interest 72°F Compressive strength at 12 hours and 60°F is 535 psi by Halliburton lab test for class "C" w/2% CaCl₂/ Circulated cement.

18. I hereby certify that the information above is true and complete to the best of my knowledge and belief.

SIGNED Jerry Sexton TITLE Agent DATE 10/10/84

ORIGINAL SIGNED BY JERRY SEXTON

APPROVED BY DISTRICT 1 SUPERVISOR TITLE _____ DATE OCT 12 1984

CONDITIONS OF APPROVAL, IF ANY: