

TEXACO INC.
NEW MEXICO "DW" STATE WELL NO. 1
GRAMA RIDGE MORROW, EAST FIELD
LEA COUNTY, NEW MEXICO

ATTACHMENT TO FORM C-101

2ND INTERMEDIATE: 7"

1st Stage Cement: 350 sxs Light w/10# gilsonite, 1/4# flocele and .5% HR-4 followed by 200 sxs Class "H" w/1/4# flocele and .3% HR-4. DV Tool @ 8000'.

2nd Stage Cement: 1200 sxs Light w/10# gilsonite, 1/4# flocele and .3% HR-4.

PRODUCTION CASING: 5"

Cement: 200 sxs 50/50 Pozmix Class "H" w/2% gel and .8% HALAD-9. The pump and plug method will be used when cementing all casing strings.

BOP diagrams are attached.