

M. B. WEIR "B" WELL NO. 13Y  
LEA COUNTY, NEW MEXICO

Continuation to Form C-101

Production Casing: continued:

1st Stage (continued): Class "H" w/1/4# Flocele plus .6%  
Halad-9 (15.6 ppg, 1.18 cu. ft./sx.).

2nd Stage: 700 sacks Light Weight w/1/4# Flocele (12.4 ppg,  
2.00 cu. ft./sx.). DV Tool at 5250'.