

Circulated hole with rig pump for 45 minutes and cemented as follows:

Pumped 15 barrels fresh water.

Mixed and pumped 2000 sacks Howco Lite Premium Plus cement with 15# salt/sk., and 1/4# flocele/sk. (2.16 cu.ft./sk. yield, 12.7#/gallon).

Tailed in with 250 sacks Premium Plus cement with 2% CACL₂ (1.32 cu.ft./sk. yield, 14.8#/gallon).

Displaced with 346 barrels fresh water.

Plug down at 4:00 AM July 11, 1991.

Circulated 150 sacks cement to reserve pit.

Pressure tested BOP to 5000 psig.

Pressure tested casing to 1500 psig.

Waited on cement a total of 25 hours.