

P.02

FAX NO. 15053933132

DOWELL HOBBS

FEB-27-96 TUE 17:19

PROJECT NO.: 20426035
 DATE: 2-13-96
 PRESSURE: 3,000
 TEMPERATURE: 70°F

CEMENT: LSG + 27.51 @ 14.8 lbs

ULTRASONIC
 CEMENT ANALYZER
 DOWELL SCHLUMBERGER

INITIAL SET: 50 0 1:34
 STRENGTH 1: 500 0 3:57
 STRENGTH 2: 19999
 CURR. STR.: 2239 0 25:34

