


PROJECT NO.: 27826-035
 DATE: 2-13-96
 PRESSURE: 3,000
 TEMPERATURE: 70°F

ULTRASONIC
 CEMENT ANALYZER
 DOWELL SCHLUMBERGER

INITIAL SET: 50 0 1:34
 STRENGTH 1: 500 0 3:57
 STRENGTH 2: 19999
 CURR. STR: 2239 0 25:34

CEMENT: LSC + 27.51 @ 14.8 deg



Received
Hoobs
OCD

2000-08-15