

Well Name: Britt B No. 33

### CEMENTING PROGRAM

#### Surface Casing String:

LEAD 225 sxs Class C Mixed at 12.7 ppg  
Additives 65:35:6 Poz + 2% CaCl<sub>2</sub> + 1/4 #/sx Celloflake

TAIL 100 sxs Class C Mixed at 14.8 ppg  
Additives 2% CaCl<sub>2</sub>

#### Intermediate Casing String:

##### 1st Stage

LEAD \_\_\_\_\_ sxs Class \_\_\_\_\_ Mixed at \_\_\_\_\_ ppg  
Additives \_\_\_\_\_

TAIL \_\_\_\_\_ sxs Class \_\_\_\_\_ Mixed at \_\_\_\_\_ ppg  
Additives \_\_\_\_\_  
Percent free water \_\_\_\_\_ Water Loss \_\_\_\_\_ cc

##### 2nd Stage

LEAD \_\_\_\_\_ sxs Class \_\_\_\_\_ Mixed at \_\_\_\_\_ ppg  
Additives \_\_\_\_\_

TAIL \_\_\_\_\_ sxs Class \_\_\_\_\_ Mixed at \_\_\_\_\_ ppg  
Additives \_\_\_\_\_  
Percent free water \_\_\_\_\_ Water Loss \_\_\_\_\_ cc

#### Production Casing String:

##### 1st Stage

LEAD 400 sxs Class C Mixed at 12.0 ppg  
Additives 16% Gel + 0.2% A-5 + 0.3% CD-320 + .3% SMS

TAIL 350 sxs Class C Mixed at 14.8 ppg  
Additives 1.1% FL-62 + 2% BA-90 + 1.5% A-5 + 0.3% CD-32 + 0.2% SMS  
Percent free water 0 Water Loss 51 cc

##### 2nd Stage

LEAD \_\_\_\_\_ sxs Class \_\_\_\_\_ Mixed at \_\_\_\_\_ ppg  
Additives \_\_\_\_\_

TAIL \_\_\_\_\_ sxs Class \_\_\_\_\_ Mixed at \_\_\_\_\_ ppg  
Additives \_\_\_\_\_  
Percent free water \_\_\_\_\_ Water Loss \_\_\_\_\_ cc

