Location:	1980' FNL & 660' FWL, Sec. 8, T 22S, R 36E, Unit Ltr 'E', Lea County, New Mexico					
Casing Program	m:					
Surface:						
Lead:	140	sacks	Class C	Mixed at	11.8	ppg
Additives:	2% CACL2	+ 0.25 pps Cello	-Flakes + 6% Bento	nite		<u> </u>
Tail :	100	_ sacks	Class C	Mixed at	14.8	ppg
Additives:	2% CACL2					
Production						
Lead:	390	sacks	Class C	Mixed at	12.4	ppg
Additves 3	5:65 Poz (Fh	y Ash) + 5% CA(CL2 + 6% Bentonite			· · · · · · · · · · · · · · · · · · ·
- Tail:	100	xacks	Class C	Mixed at	14.8	ppg