Vell Name:	State "A" A	/C 2 # 78	·			
_ocation:	1980' FNL & 660' FWL, Sec.5, T 22S, R 36E, Unit Ltr 'E', Lea County, New Mexico					
Casing Program	n:					
Surface:						
Lead:	140	sacks	Class C	Mixed at	11,8	ppg
Additives:	2% CACL2	+ 0.25 pps Cello	p-Flakes + 6% Bentonite	· · · · · · · · · · · · · · · · · · ·		
Tail:	100	_ sacks _	Class C	Mixed at	14.8	ppg
Additives:	2% CACL2		······································			
Production						
Lead: _	390	sacks	Class C	Mixed at _	12.4	ppg
Additves 3	5:65 Poz (Fl	y Ash) + 5% CA	CL2 + 6% Bentonite		<del></del>	
Tail: _	100	sacks	Class C	Mixed at _	14.8	ppg
Additives: 3%	6 Potassium (	Chloride + 2% C	D-32 +_ 0.6% FL-62			