

**SEMU #158****PROPOSED CASING & CEMENT PLAN**

|                                                |                         |                                                                           |             |
|------------------------------------------------|-------------------------|---------------------------------------------------------------------------|-------------|
| Surface casing size:                           | 8-5/8", 24#, J-55, ST&C | Casing OD:                                                                | 8.625 in    |
| Surface casing depth:                          | 1,500 ft                | Casing ID:                                                                | 8.097 in    |
| Hole size:                                     | 12.25 in                | Shoe jt length:                                                           | 40 ft       |
| Static temperature:                            | 89 deg F                | Lead Excess:                                                              | 101 %       |
| Circulating temperature:                       | 85 deg F                | Tail Excess:                                                              | 106 %       |
| Lead:                                          | 465 sx                  | CI C + 0.25 pps Cello Flake + 0.005 gps FP-6L<br>+ 2% Sodium Metasilicate |             |
| Tail:                                          | 200 sx                  | CI C + 2% CaCl + 0.005 gps FP-6L                                          |             |
| <b>Properties</b>                              |                         | <b>Lead</b>                                                               | <b>Tail</b> |
| Slurry Weight (ppg)                            |                         | 12.4                                                                      | 14.8        |
| Slurry Yield (cfps)                            |                         | 2.15                                                                      | 1.34        |
| Mix Water (gps)                                |                         | 12.33                                                                     | 6.35        |
| Pump time - 70 BC (HH:MM)                      |                         | 6:25                                                                      | 2:20        |
| Free Water (mls) @ 80 deg F @ 90 deg angle     |                         | 0                                                                         | 0           |
| Fluid Loss (cc/30 min) @ 1000 psi and 80 deg F |                         | 854                                                                       | 900         |
| Compressive Strength (psi)                     |                         |                                                                           |             |
| 12 hrs @                                       | 89 deg F                | 124                                                                       | 1200        |
| 24 hrs @                                       | 89 deg F                | 250                                                                       | 2500        |

|                                                |                        |                                                                                           |             |
|------------------------------------------------|------------------------|-------------------------------------------------------------------------------------------|-------------|
| Production casing size:                        | 5-1/2", 17#, J55, LT&C | Casing OD:                                                                                | 5.500 in    |
| Production casing depth:                       | 7,975 ft               | Casing ID:                                                                                | 4.892 in    |
| Hole size:                                     | 7.875 in               | Shoe jt length:                                                                           | 80 ft       |
| Static temperature:                            | 127 deg F              | Lead Excess:                                                                              | 51 %        |
| Circulating temperature:                       | 121 deg F              | Tail Excess:                                                                              | 51 %        |
| Lead:                                          | 565 sx                 | 50:50 Poz:Cl C + 5% bwow NaCl + 0.25 pps<br>Cello Flake + 0.005 gps FP-6L + 10% Bentonite |             |
| Tail:                                          | 425 sx                 | 15:61:11 Poz:Cl C:CSE + 5% bwow NaCl +<br>1% FL-62 + 0.005 gps FP-6L                      |             |
| <b>Properties</b>                              |                        |                                                                                           |             |
|                                                |                        | <b>Lead</b>                                                                               | <b>Tail</b> |
| Slurry Weight (ppg)                            |                        | 11.85                                                                                     | 13.6        |
| Slurry Yield (cfps)                            |                        | 2.41                                                                                      | 1.49        |
| Mix Water (gps)                                |                        | 13.79                                                                                     | 7.31        |
| Pump time - 70 BC (HH:MM)                      |                        | 2:58                                                                                      | 2:31        |
| Free Water (mls) @ 80 deg F @ 90 deg angle     |                        | 1                                                                                         | 0           |
| Fluid Loss (cc/30 min) @ 1000 psi and 80 deg F |                        | 792                                                                                       | 62          |
| Compressive Strength (psi)                     |                        |                                                                                           |             |
| 12 hrs @                                       | 124 deg F              | 50                                                                                        | 1013        |
| 24 hrs @                                       | 124 deg F              | 175                                                                                       | 1875        |