

Texaco Producing Inc.
Bilbrey "32" State Com Well No. 1

CEMENTING PROGRAM

20" Conductor: Redi-mix

13 3/8" Casing: Circulate to surface using 950 SX Class H with 2% Cacl₂ and 1/4# Flocele (15.6ppg, 1.19f₃/s, 5.2gw/s). F/B 200 SX Class H with 2% Cacl₂ (15.6ppg, 1.19f₃/s, 5.2gw/s).

9 5/8" Casing: Circulate to surface using 1500 SX 35/65 Poz Class H with 6% Gel & 5% Salt (12.8ppg, 1.87f₃/s, 9.9gw/s). F/B 250 SX Class H (15.6ppg, 1.18f₃/s, 5.2gw/s).

7" Casing: Circulate to surface using 200 SX 35/65 Poz Class H with 6% Gel, 5% Salt, 0.3% HR-4 (12.8ppg, 1.87f₃/s, 9.9gw/s). F/B 200 SX Class H with 0.2% HR-7 (15.6ppg, 1.18f₃/s, 5.2gw/s).

DV Tool @ 9000': 2nd Stage - 1000 SX 35/65 Poz Class H with 6% Gel, 5% Salt, 1/4# Flocele (12.8ppg, 1.87f₃/s, 9.9gw/s).

5" Liner: 200 SX Class H with 5% Salt, 0.3% Halad 22-A & 0.1% HR-7 (15.6ppg, 1.20f₃/s, 5.2gw/s).

Sqz Top @ 11700': 300 SX Class H with 5% Salt, 0.3% Halad 22-A & 0.1% HR-7 (15.6ppg, 1.20f₃/s, 5.2gw/s).

RECEIVED

APR 26 1950

OCO
MOBBS OFFICE