WELL NAME: MEYER B - 4 No. 31

LOCATION : 2930' FNL 2087' FWL Sec. 4, T-21S, R-36E

Casing Program

Surface	8-5/8	inch	in	12-1/4"	hole	a+	420	<i>.</i>
Prod	5-1/2	inch	in	7-7/8"	hole		420	IC.
Cementing Program	n					ac	3580	Ĩt.

Surface

Lead 250 · sxs Additives 4% Gel Tail 100 sxs Additives 2% A7P	Class	С	Mixed	at <u>13.7</u> ppg
Additives 2% A7P	Class_	С	Mixed	at 14.8 ppg

Production (first stage)

Lead 500 sxs Class C-Lite Mixed at 12.7 ppg Additives 65:35:6 with 5PPS Salt + .2% SMS Tail 350 sxs Class C Mixed at 14.6 ppg Additives 1.1% Flo-Bloc + .2% SMS Percent free water 0 Water loss 50 CC

ANTICIPATED DRILLING TIME: 6 Days

ANTICIPATED BOTTOM HOLE PRESSURE: 500 psi



OFFICE