

WELL NAME: Meyer A-1 No. 22

LOCATION : Sec 8-L, T-21S, R-36E

### Casing Program

Surface 8-5/8 inch in 12-1/4" hole at 420 ft.

Prod 4-1/2 inch in 7-7/8" hole at 3750 ft.

### Cementing Program

#### Surface

Lead 250 sxs Class C Mixed at 13.7 ppg  
Additives 4% Gel + 2% A7P  
Tail 100 sxs Class C Mixed at 14.8 ppg  
Additives 2% A7P

#### Production (first stage)

Lead 560 sxs Class C-Lite Mixed at 12.7 ppg  
Additives 65:35:6 with 5PPS Salt + .2% SMS  
Tail 400 sxs Class C Mixed at 14.6 ppg  
Additives 1.1% Flo-Bloc + .2% SMS  
Percent free water 0 Water loss 50 cc