

NO. OF COPIES RECEIVED		
DISTRIBUTION		
SANTA FE		
FILE		
U.S.G.S.		
LAND OFFICE		
OPERATOR		

NEW MEXICO OIL CONSERVATION COMMISSION

Form C-103
Supersedes Old
C-102 and C-103
Effective 1-1-65

SUNDRY NOTICES AND REPORTS ON WELLS <small>(DO NOT USE THIS FORM FOR PROPOSALS TO DRILL OR TO DEEPEN OR PLUG BACK TO A DIFFERENT RESERVOIR. USE "APPLICATION FOR PERMIT -" (FORM C-101) FOR SUCH PROPOSALS.)</small>		5a. Indicate Type of Lease State <input type="checkbox"/> Fee <input checked="" type="checkbox"/>
1. <input checked="" type="checkbox"/> OIL WELL <input type="checkbox"/> GAS WELL <input type="checkbox"/> OTHER-		5. State Oil & Gas Lease No.
2. Name of Operator Morris R. Antweil		7. Unit Agreement Name
3. Address of Operator P. O. Box 2010, Hobbs, New Mexico 88240		8. Farm or Lease Name Shell "G"
4. Location of Well UNIT LETTER P , 330 FEET FROM THE South LINE AND 330 FEET FROM THE East LINE, SECTION 8 TOWNSHIP 22S RANGE 37E NMPM.		9. Well No. 1
15. Elevation (Show whether DF, RT, GR, etc.) 3411 K.B.		10. Field and Pool, or Wildcat Undesignated
12. County Lea		

16. Check Appropriate Box To Indicate Nature of Notice, Report or Other Data NOTICE OF INTENTION TO:		SUBSEQUENT REPORT OF:	
PERFORM REMEDIAL WORK <input type="checkbox"/> TEMPORARILY ABANDON <input type="checkbox"/> PULL OR ALTER CASING <input type="checkbox"/> OTHER <input type="checkbox"/>	PLUG AND ABANDON <input type="checkbox"/> CHANGE PLANS <input type="checkbox"/>	REMEDIAL WORK <input type="checkbox"/> COMMENCE DRILLING OPNS. <input type="checkbox"/> CASING TEST AND CEMENT JOB <input checked="" type="checkbox"/> OTHER <input type="checkbox"/>	ALTERING CASING <input type="checkbox"/> PLUG AND ABANDONMENT <input type="checkbox"/>

17. Describe Proposed or Completed Operations (Clearly state all pertinent details, and give pertinent dates, including estimated date of starting any proposed work) SEE RULE 1103.

Well spudded 7:00 P.M. Oct. 3, 1969. Ran and set 8-5/8" 32#/ft surface casing at 1193'. Cemented with 185 sxs. Class "C" cement plus 4% gel and 1/4# Floseal per sax and 200 sxs. Class "C" cement with 2% Calcium Chloride plus 1/4 Floseal per sax. Cement Circulated. Tested casing 500 psi. for 30 minutes. No decline in pressure. Drilling ahead.

18. I hereby certify that the information above is true and complete to the best of my knowledge and belief.		
SIGNED <i>[Signature]</i>	TITLE Agent	DATE 10/10/69
APPROVED BY <i>[Signature]</i>	TITLE	DATE
CONDITIONS OF APPROVAL, IF ANY:		