

CEMENT

TYPE OF STRING INTERVAL (FT) FROM-TO TYPE MIX	GEL%	SALT%	CaCl ₂	SLURRY WEIGHT LB./GAL.	SLURRY YIELD OF/SKX	TOTAL AMT. REQUIRED SKX/CF	FILL UP	BHT	SIZE	REMARKS
(S) 0'-1600' Class 'C' 4%			2%	13.50	1.88	572/1074	circulate		12 1/4"	100% excess
Class 'C'			2%	14.80	1.32	184/248				
(P) 0'-3880' *Class 'C' Light 18%				13.20	1.92	(430) 828	circulate		7 7/8"	100% excess
Class 'C'			2%	14.80	1.32	(200) 264				

Note: Reciprocate production casing while cementing.

*Class 'C' light: Examples - BJ light, Howco light, Dowell light.

Cement volumes to be recalculated after caliper run.