

UNITED STATES
DEPARTMENT OF THE INTERIOR
GEOLOGICAL SURVEYSUBMIT IN TRIPLICATE*
(Other instructions re-
verse side)Form approved.
Budget Bureau No. 42-R1424.

5. LEASE DESIGNATION AND SERIAL NO.

NM 0552659-A

6. IF INDIAN, ALLOTTEE OR TRIBE NAME

7. UNIT AGREEMENT NAME

8. FARM OR LEASE NAME

Curry Federal

9. WELL NO.

3

10. FIELD AND POOL, OR WILDCAT

Antelope Ridge (Morrow)

11. SEC., T., R., M., OR BLK. AND
SURVEY OR AREA

Sec. 22, T23S, R34E

12. COUNTY OR PARISH

Lea

13. STATE

New Mexico

1. OIL ☐ GAS ☒ OTHER ☐
WELL WELL

2. NAME OF OPERATOR

Curry Resources

3. ADDRESS OF OPERATOR

P. O. Box 5596, Midland, Texas 79704

4. LOCATION OF WELL (Report location clearly and in accordance with any State requirements.*
See also space 17 below.)
At surface

1680' FSL and 760' FEL of Section 22, T23S, R34E

14. PERMIT NO.

15. ELEVATIONS (Show whether DF, RT, GR, etc.)

GL 3415.5

16. Check Appropriate Box To Indicate Nature of Notice, Report, or Other Data

NOTICE OF INTENTION TO:

TEST WATER SHUT-OFF

FRACTURE TREAT

SHOOT OR ACIDIZE

REPAIR WELL

(Other)

PULL OR ALTER CASING

MULTIPLE COMPLETE

ABANDON*

CHANGE PLANS

SUBSEQUENT REPORT OF:

WATER SHUT-OFF

FRACTURE TREATMENT

SHOOTING OR ACIDIZING

(Other) Running Casing

REPAIRING WELL

ALTERING CASING

ABANDONMENT*

(NOTE: Report results of multiple completion on Well
Completion or Recompletion Report and Log form.)

17. DESCRIBE PROPOSED OR COMPLETED OPERATIONS (Clearly state all pertinent details, and give pertinent dates, including estimated date of starting any proposed work. If well is directionally drilled, give subsurface locations and measured and true vertical depths for all markers and zones pertinent to this work.)*

The following casing strings have been run and cemented in the subject well.

SURFACE CASING

15 jts., 13 3/8" OD, 8RD, 68 #/ft., LT & C, new casing.

Cemented with 600 sacks Class "C" cement, 4% gel, 1/4 #/sack flocele with 2% CaCl2 followed with 150 sacks of Class "C", 2% gel, 2% CaCl2 circulated out 275 sacks excess. WOC 20 hrs total.

INTERMEDIATE CASING

120 jts., 10 3/4 " OD, 8 Rd, 45.5 and 51 #/ft., LT & C, new casing.

Cemented in 2 stages with DV tool set at 880'.

1st stage: 700 sacks Class "C", 8% gel, 1/4 #/sack Flocele, 2% CaCl2, 5 #/sack gilsonite, followed by 300 sacks Class "C", 2% gel, 2% CaCl2, cement circulated.

2nd stage: 200 sacks Class "C", 8% gel, 1/4 # Flocele, 2% CaCl2, 5 #/sack gilsonite followed with 50 sacks Class "C", 2% CaCl2, 2% gel. Circulated cement. Drilled out DV tool and pressured up to 2500 psi. Tested OK.

18. I hereby certify that the foregoing is true and correct

SIGNED

TITLE

DATE

(This space for Federal or State Office Use)
ACCEPTED FOR RECORD

APPROVED BY

TITLE

DATE

CONDITIONS OF APPROVAL

AUG 22 1984

NEW MEXICO *See Instructions on Reverse Side

RECEIVED

AUG 24 1984

CCD
HOBBS OFFICE