ell Name:	State "A" A/C 1 # 128 1980' FSL & 1830' FWL, Sec.13, T 23S, R 36E, Unit Ltr 'K', Lea Co					
ocation:					ounty, New Mexico	
asing Program	n:					
Surface:						
Lead:	140	sacks	Class C	Mixed at	11.8	ppg
Additives:	2% CACL2 + 0.25 pps Cello-Flakes + 6% Bentonite					
<b>Tail</b> :	100	sacks	Class C	Mixed at	14.8	ppg
Additives:	2% CACL2			<b></b>		
Production						
Lead: _	390	sacks	Class C	Mixed at	12.4	ppg
Additves 3	35:65 Poz (Fly Ash) + 5% CACL2 + 6% Bentonite					
Tail:	100	sacks	Class C	Mixed at	14.8	ppg