

**Well Name:** State "A" A/C 1 # 132

**Location:** 660' FSL & 660' FWL, Sec 21, T 23S, R 36E, (M), Lea County

**Casing Program:**

**Surface:** 8 5/8" Casing in 12 1/4" Hole at 600 ft.

**Production:** 5 1/2" Casing in 7 7/8" Hole at 4500 ft.

**Cementing Program:**

• **Surface:**

Lead: 140 sacks Class C Mixed at 11.8 PPG  
Additives: 2% CACL2 + 0.25 pps Cello-Flake = 6% Bentonite.

Tail: 100 sacks Class C Mixed at 14.8 ppg  
Additives: 2% CACL2

**Production:**

Lead: 390 sacks Class C Mixed at 12.4 ppg  
Additives: 35:65 Poz (Fly Ash) = 5% CACL2 + 6% Bentonite

Tail: 100 sacks Class C Mixed at 14.8 ppg  
Additives: 3% Potassium Chloride + 2% CD-32 + 0.6% FL-62