Well Name: State "A" A/C 1 # 130

Location: 660' FSL & 660' FE L, Sec 9, T 23S, R 36E, (P) Lea County

Casing Program:

Surface: 8 5/8" Casing in 12 1/4" Hole at 600 ft.

Production: 51/2" casing in 7.7/8" Hole at 4200 ft.

Cementing Program:

Surface:

Lead: 140 sacks Class C Mixed at 11.8 PPG

Additives: 2% CACL2 + 0.25 pps Cello-Flake = 6% Bentonite.

Tail: 100 sacks Class C Mixed at 14.8 ppg

Additives: 2% CACL2

Production:

Lead: 390 sacks Class C Mixed at 12.4 ppg

Additives: 35:65 Poz (Fly Ash) = 5% CACL2 + 6% Bentonite

Tail: 100 sacks Class C Mixed at 14.8 ppg

Additives: 3% Potassium Chloride + 2% CD-32 + 0.6% FL-62