

CEMENT

TYPE OF STRING INTERVAL (FT) FROM-TO TYPE MIX	GEL%	SALT%	CaCl ₂	SLURRY WEIGHT LB./GAL.	SLURRY YIELD OF/SKX	TOTAL AMT. REQUIRED SKX/CF	FILL UP	BHT	SIZE	REMARKS
) 0'-1500' Class "C" Class "C"	4%		2%	13.50	1.88	576/974	Circulate		12 1/4"	100% Excess 1/4#/sx floccle in all cement
				14.80	1.32	200/264				
) 0'-3720' Class "C" Light Class "C"		18%	2%	13.20	1.92	462/773	Circulate		7 7/8"	100% Excess 1/4#/sx floccle in all cement
				14.80	1.32	190/251				

te: Reciprocate production casing while cementing.

*Class "C" Light - Examples: BJ Light, Howco Light, Dowell Light.

Cement volume to be recalculated after caliper run.