

Schlumberger

Dowell

CemDABE Cement Test Report

June 28, 1995

DATE OF TEST : 27-jun-1995

TEST NUMBER : NPD548300002

CUSTOMER : TEXACO
FIELD : LEA NM
WELL : R R SIMS A 6

CEMENT
Class : C
Blend :
Brand : LONESTAR
Plant : MARYNEAL

BASE FLUID
Density : 8.32 lb/gal
Volume : 6.32 gal/sk
Type : LO
Total liquid : 6.32 gal/sk

SLURRY
Density : 14.80 lb/gal
Yield : 1.32 ft³/sk

B.H.S.T. : 92.0 F

B.H.C.T. : 88.0 F

ADDITIVES		
Code	Concent.	Unit
5001	2.000	% BWOC

Rheometer type : Fann 35

Spring factor : 1.0

Bob No : 1

Rotor No : 1

Rheological model (Dial 1) : Bingham Plastic

T_y : 23.529 lb/100ft²

P_y : 15.628 cP

Correlation coefficient : 0.997

Thickening Time : 1 hr58 mn to 70 BC

API Schedule :

Set condition :

Consistometer serial number :

No Fluid Loss data available

No Free Water data available

Rheological data		
Temp. (F) :	75.0	0.0
R.P.M.	Dial 1	Dial 2
300.0	39.0	0.0
200.0	34.0	0.0
100.0	28.0	0.0
60.0	27.0	0.0
30.0	24.0	0.0
6.0	20.0	0.0
3.0	17.0	0.0
0.0	0.0	0.0
0.0	0.0	0.0
10 minutes Gel : 0.0		

Compressive strength		
PSI	Hours	Temp. (F)
600	6.0	92.0
1400	12.0	92.0
2000	24.0	92.0

Comment :

FIELD BLEND

CLASS C + 2% S-1

LOCATION WATER USED

SURFACE TAIL 1200' POD = 0:50

RECEIVED

AUG 31 1995
JUD HOBBBS
OFFICE