

Schlumberger

Dowell

CemDABE Cement Test Report

July 5, 1995

DATE OF TEST : 05-jul-1995

TEST NUMBER : NPD549900001

CUSTOMER : TEXACO
FIELD : LEA NM
WELL : R R SIMS A6

CEMENT
Class : H
Blend : 3565
Brand : LONESTAR
Plant : MARYNEAL

BASE FLUID

Density : 8.32 lb/gal
Volume : 11.95 gal/sk
Type : LO
Total liquid : 11.95 gal/sk

SLURRY

Density : 12.40 lb/gal
Yield : 2.14 ft³/sk

B.H.S.T. : 113.0 F

B.H.C.T. : 106.0 F

ADDITIVES		
Code	Concent.	Unit
D020	6.000	% BWOC
D029	0.250	% BWOC
D044	5.000	% BWOW

Rheometer type : Fann 35

Spring factor : 1.0

Bob No : 1

Rotor No : 1

Rheological model (Dial 1) : Bingham Plastic

T_y : 27.102 lbf/100ft²

P_v : 9.038 cP

Correlation coefficient : 1.000

Thickening Time : 8 hr28 mn to 70 BC

API Schedule :

Set condition :

Consistometer serial number :

No Fluid Loss data available

No Free Water data available

Rheological data		
Temp. (F) :	75.0	0.0
R.P.M.	Dial 1	Dial 2
300.0	36.0	0.0
200.0	33.0	0.0
100.0	30.0	0.0
60.0	29.0	0.0
30.0	28.0	0.0
6.0	24.0	0.0
3.0	15.0	0.0
0.0	0.0	0.0
0.0	0.0	0.0
10 minutes Gel : 0.0		

Compressive strength		
PSI	Hours	Temp. (F)
115	6.0	113.0
275	12.0	113.0
425	24.0	113.0

Comment :

FIELD BLEND

35/65 POZ/H + 6% D20 + 5% D44 (BWOW) + 0.25PPS D29

LOCATION WATER USED

LONG STRING LEAD 5450' POD = 4:18

P.04

FAX NO. 15053933132

POWELL HOBBS

JUL-06-95 THU 21:06

RECEIVED
AUG 6 1 1946
OCD HOEBS
OFFICE