

PAGE START DATE: 5/ 6/95
PAGE START TIME: 14:51: 0
DATA FILE: 8

DELTA TIME HRS	DEPTH FEET	TEMPERATURE 'F	COMMENTS
0.000	20.00	76.00	
0.558	1250.00	81.00	BREAK
0.600	1379.00	90.75	
0.617	1434.00	89.00	
0.633	1492.00	92.50	
0.642	1520.00	90.00	
0.650	1548.00	91.50	
0.667	1607.00	90.50	
0.675	1637.00	92.50	
0.717	1794.00	93.25	
0.725	1824.00	91.75	
0.733	1855.00	92.75	
0.742	1889.00	91.50	
0.758	1959.00	94.00	
0.800	2135.00	95.50	
0.808	2170.00	91.75	
0.817	2206.00	95.00	
0.825	2243.00	91.00	
0.833	2280.00	95.25	
0.842	2320.00	92.75	
0.858	2401.00	98.50	
0.867	2443.00	93.50	
0.883	2523.00	104.00	
0.925	2735.00	96.00	
0.950	2873.00	104.50	
0.975	3008.00	100.25	
0.983	3054.00	100.25	
0.992	3104.00	99.50	
1.000	3155.00	100.25	
1.008	3203.00	98.50	
1.017	3252.00	99.50	
1.025	3300.00	98.50	
1.042	3401.00	99.50	
1.083	3654.00	99.00	
1.117	3752.00	100.25	M.D.R.

DATE AND TIME CEMENT JOB COMPLETE:

MAY 5, 1995 @ 11:00 PM

DATE AND TIME SURVEY MADE:

MAY 6, 1995 @ 2:45 PM

AMOUNT AND TYPE CEMENT USED:

350 SACKS CLASS C LIGHT WEIGHT
FOLLOWED BY 350 SACKS CLASS C
PREMIUM RUN BEHIND 3800 FEET OF
5½" CASING IN A 7-7/8" HOLE.

DEPTH FIGURED FROM:

GROUND LEVEL