

WELL NAME: Cooper 8 No. 2

LOCATION : 860' FSL, 1980' FWL, Sec 8, T24S, R37E

Casing Program

Surface 8-5/8 inch in 12-1/4" hole at 420 ft.

Prod 5-1/2 inch in 7-7/8" hole at 3270 ft.

Cementing Program

Surface

Lead 250 sxs Class C Mixed at 13.7 ppg

Additives 4% Gel + 2% A7P

Tail 100 sxs Class C Mixed at 14.8 ppg

Additives 2% A7P

Production (first stage)

Lead 500 sxs Class C-Lite Mixed at 12.7 ppg

Additives 65:35:6 with 5PPS Salt + .2% SMS

Tail 350 sxs Class C Mixed at 14.6 ppg

Additives 1.1% Flo-Bloc + .2% SMS

Percent free water 0 Water loss 50 cc

**RECEIVED**

JAN 04 1995

OCD HOBBS  
OFFICE